

POLYMER SOLUTIONS

PA 2201

Material Data Sheet

PA 2201

Product Description

PA 2201, based on polyamide 12, offers a wide range of applications thanks to its very balanced property profile. Components made from this pigment free polyamide 12 powder are whitish, slightly translucent. With properties otherwise comparable to PA 2200 – strength, rigidity and good chemical resistance – parts made from PA 2201 can be approved for use in the medical industry.

MAIN CHARACTERISTICS

- Balanced property profile
- Multipurpose material

TYPICAL APPLICATIONS

- Surgery cutting guides and bone models for the medical industry
- Functional parts for prototyping, that include hinges or threads

MECHANICAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Tensile Modulus			ISO 527-1/-2
X Orientation	1700 / -	MPa	
Y Orientation	1700 / -	MPa	
Tensile Strength			ISO 527-1/-2
X Orientation	48 / -	MPa	
Y Orientation	48 / -	MPa	
Nominal Strain at Break			ISO 527-1/-2
X Orientation	15 / -	%	
Flexural Modulus			ISO 178
X Orientation	1500 / -	MPa	
Flexural Strength			ISO 178
X Orientation	58 / -	MPa	
Charpy Impact Strength (+23°C)			ISO 179/1eU
X Orientation	53 / -	kJ/m ²	
Charpy Notched Impact Strength (+23°C)			ISO 179/1eA
X Orientation	4.4 / -	-	
Izod Impact Strength (+23°C)			ISO 180/1U
X Orientation	33 / -	kJ/m ²	
Izod Notched Impact Strength (+23°C)			ISO 180/1A
X Orientation	4.4 / -	kJ/m ²	
Shore D Hardness			ISO 7619-1
X Orientation	75 / -	-	
Ball Indentation Hardness			ISO 2039-1
X Orientation	78 / -	MPa	
THERMAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Melting Temperature	176	°C	ISO 11357-1/-3
Vicat Softening Temperature			ISO 306/A50
X Orientation	181	°C	
Vicat Softening Temperature			ISO 306/B50
X Orientation	163	°C	
OTHER PROPERTIES	VALUE	UNIT	TEST STANDARD
Density	0.93	g/cm ³	EOS Method
Powder Color	natural	-	-
Components Color	natural	-	-

HEADQUARTERS

EOS GmbH
Electro Optical Systems

Robert-Stirling-Ring 1
82152 Krailling / Munich
Germany

Tel.: +49 89 893 36-0
Email: info@eos.info
URL: www.eos.info

This powder has not been developed, tested or certified as a medical device according to Directive 93/42/EEC (MDD) or Regulation (EU) 2017/745 (MDR) and is not intended to be used as a medical device, in particular for the purposes specified in Art. 2 No. 1 MDR. Insofar as you intend to use the powder as raw material for the manufacture of pharmaceutical products or medical devices (e.g. as raw material which as a material must meet the requirements of Annex 1, Chapter II MDR), the responsibility and liability for all analyses, tests, evaluations, procedures, risk assessments, conformity assessments, approval and certification procedures as well as for all other official and regulatory measures required for this purpose shall lie solely with you both with regard to the pharmaceutical product and/or medical device manufactured by you and with regard to the properties, suitability, testing, evaluation, risk assessment, other requirements for use of the powder as raw material. In this respect, the limitations of liability pursuant to our General Terms and Conditions and the system sales or material contracts shall apply.

Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein. This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

The achievement of certain part properties as well as the assessment of the suitability of this material for a specific purpose is the sole responsibility of the user. Any information given herein is subject to change without notice.

Status as of 06.10.2025. Subject to technical modifications. EOS is certified according to ISO 9001.

EOS®, Additive Minds®, Alumide®, AMQ®, CarbonMide®, DirectMetal®, DMLS®, EOSAME®, EOSINT®, EOSIZE®, EOSPACE®, EOSPRINT®, EOSTATE®, EOSTYLE®, FORMIGA®, LaserProFusion®, PA 2200®, PrimeCast® and PrimePart® are registered trademarks of EOS GmbH Electro Optical Systems in some countries. For more information visit www.eos.info/trademarks.